


Radiation	Type	Technology	Electrodes
Infrared	DDH	AlGaAs/AlGaAs	N (cathode) up

 <p>PoC-05</p>	typ. dimensions (µm)
	<p>typ. thickness 180 µm</p> <p>cathode gold alloy, 1.5 µm</p> <p>anode gold alloy, 0.5 µm structured, 25% covered</p>

Optical and Electrical Characteristics

$T_{amb} = 25^{\circ}\text{C}$, unless otherwise specified

Parameter	Test conditions	Symbol	Min	Typ	Max	Unit
Forward voltage	$I_F = 20 \text{ mA}$	V_F		1.3	1.5	V
Forward voltage ¹	$I_F = 350 \text{ mA}$	V_F		1.5	1.8	V
Reverse voltage	$I_R = 100 \text{ µA}$	V_R	5			V
Radiant power	$I_F = 20 \text{ mA}$	Φ_e	3.5	5		mW
Radiant power ¹	$I_F = 350 \text{ mA}$	Φ_e	70	90		mW
Peak wavelength	$I_F = 20 \text{ mA}$	λ_P	860	870	880	nm
Spectral bandwidth at 50%	$I_F = 20 \text{ mA}$	$\Delta\lambda_{0.5}$		35		nm
Switching time	$I_F = 20 \text{ mA}$	t_r, t_f		20		ns

¹Measured on bare chip glued on a $\varnothing 8 \times 1 \text{ mm}$ Cu header with JENOPTIK Polymer Systems equipment

Labeling

Type	Lot	$\Phi_e(\text{typ})$ [mW]	$V_F(\text{typ})$ [V]	$\lambda_P(\text{typ})$ [nm]	Quantity
ELC-870-21					

Packing: Chips on adhesive film with wire-bond side on top

Environmental		Symbol	Min	Typ	Max	Unit
Storage Temperature	on Blue Tape	T_{STG}	15		30	$^{\circ}\text{C}$
Storage Relative Humidity	on Blue Tape	RH_{STG}	40		75	% RH
Storage Time	on Blue Tape	t_{STG}			1	year

We reserve the right to make changes to improve technical design and may do so without further notice.

Parameters can vary in different applications. All operating parameters must be validated for each customer application by the customer.

JENOPTIK Polymer Systems GmbH, D-12555 Berlin, Köpenicker Str.325 b, Haus 201

Tel.: +49-30-6576 2543, Fax : +49-30-6576 2545